



Specification of Precision Tweezers

General

Made of Stainless steel

(Low carbon austenitic steel material number 1.4404 DIN X2CrNiMo 17-12-2 AISI number 316L Thyssen steel)

Contains from 16.5 to 18.5 wt% chromium and has important quantities of nickel and molybdenum as additional alloying elements.

Non-magnetisable.

Good corrosion resistance and toughness are primary requirements.

Typical applications include tools and equipment for laboratory and medical applications in mild aggressive chemical environments.

Composition:

Component	Wt %	Component	Wt%	Component	Wt%
C	<0.03	Si	<1.0	Mn	<2.0
P	<0.045	S	<0.03	Cr	16.5 – 18.5
Mo	2.0-2.5	Ni	10.0 – 13.00		

Mechanical Properties:

State	Annealed
Density	8.0 g/cm ³
Hardness HB30	<215
Hardness Rockwell B	79
Tensile strength ultimate	500-700 MPa
Tensile strength yield	290
0.2% Yield stress	>200 MPa
Elongation, break	40%
Modulus of elasticity	200 GPa



Thermal Properties:

Coef of lin therm expansion	16.0 E-6/degrees C	20-100 degrees C
Coef of lint herm expansion	17.0 E-6/ degrees C	20-300 degrees C
Specific heat capacity:	0.50J (g.K)	
Thermal conductivity:	15W/m.K)	

Continuous use temperature: 300 degrees C

Max service temperature, air 825 degrees C

Electrical Properties

Resistivity: 0.75 E-4 ohm.cm

The information contained within this spec sheet is for guidance only. We make no warranties expressed or implied and assume no liability regarding any use of this information. (Review June 15)

