

Specification of Precision Tweezers

General

Made of Stainless steel

(Low carbon austenitic steel material number 1.4404 DIN X2CrNiMo 17-12-2 AISI number 316L Thyssen steel) Contains from 16.5 to 18.5 wt% chromium and has important quantities of nickel and molybdenum as additional alloying elements.

Non-magnetisable.

Good corrosion resistance and toughness are primary requirements.

Typical applications include tools and equipment for laboratory and medical applications in mild aggressive chemical environments.

Composition:

Component	Wt %	Component	Wt%	Component	Wt%
С	<0.03	Si	<1.0	Mn	<2.0
Р	<0.045	S	<0.03	Cr	16.5 – 18.5
Мо	2.0-2.5	Ni	10.0 - 13.00		

Mechanical Properties:

State Annealed
Density 8.0 g/cm3
Hardness HB30 <215
Hardness Rockwell B 79

Tensile strength ultimate 500-700 MPa

Tensile strength yield 290
0.2% Yield stress >200 MPa
Elongation, break 40%
Modulus of elasticity 200 GPa



Thermal Properties:

Coef of lin therm expansion 16.0 E-6/degrees C Coef of lint herm expansion 17.0 E-6/ degrees C

Specific heat capacity: 0.50J (g.K)Thermal conductivity: 15W/m.K)

Continuous use temperature: 300 degrees C

Max service temperature, air 825 degrees C

Electrical Properties

Resistivity: 0.75 E-4 ohm.cm

The information contained within this spec sheet is for guidance only. We make no warranties expressed or implied and assume no liability regarding any use of this information.(Re-view July 15)





20-100 degrees C 20-300 degrees C